



Direct Roving 312 for Filament Winding, Weaving and Pultrusion

Direct Roving 312 is an E-glass roving produced by directly winding a certain number of individual fibers from the bushing without twist. It is coated with a silane-based size and is designed for the filament winding, weaving and pultrusion processes.

SPECIFICATIONS

Type of Glass
E-Glass (E)

Type of Fiberglass
Direct Roving (DR)

Standard
Linear Mass Densities
200 to 9600
grams per metre (Tex)

Filament Diameter
13 to 30 microns

Most Common Sizes
EDR13-2400-312

FEATURES

- Compatible with multiple resin systems
- Complete and fast wet-out
- Good mechanical properties
- Good weaving properties
- Low fuzz

RESIN COMPATIBILITY:

- Epoxy (EP)
- Polyester

USES:

- Boats/yachts
- Chemical tanks
- FRP pipes
- Geotechnical gratings
- Pressure vessels and profiles
- Wind blades

TECHNICAL PARAMETERS

Linear Density (%)
ISO 1889
± 5

Moisture Content (%)
ISO 3344
≤ 0.10

Size Content (%)
ISO 1887
0.60 ± 0.15

Breakage Strength (N/tex)
ISO 3341
≥ 0.40

MECHANICAL PROPERTIES

Tensile Strength
ASTM D2343
2513 MPa


Tensile Modulus
ASTM D2343
79164 MPa

Shear Strength
ASTM D2344
67 MPa

Shear Strength Retention
(72 hr. boiling)
93%

NOMENCLATURE

EDR00-000-000



PACKAGING STORAGE


Direct Roving 312 for Filament Winding, Weaving and Pultrusion

PACKAGING


Doffs can be packed on pallets or in small cardboard boxes.



Doff



3-Layer Pallet
12 doffs per Layer



3-Layer Pallet
16 doffs per Layer

Doff:	270	310
Doff outside diameter	270 mm (10.6 in)	310 mm (12.2 in)
Doff inside diameter	160 mm (6.3 in)	160 mm (6.3 in)
Doff height	260 mm (10 in)	260 mm (10 in)
Doff weight	15.6 kg (34.4 lb)	22 kg (48.5 lb)

Pallet:

Number of layers per pallet	3	4	3	4
Number of doffs per layer	16	16	12	12
Number of doffs per pallet	48	64	36	48
Net weight	750 (1653.4 lb)	1000 kg (2204.6 lb)	792 kg (1746 lb)	1056 kg (2328 lb)
Length	1120 mm (44 in)	1120 mm (44 in)	1270 mm (50 in)	1270 mm (50 in)
Width	1120 mm (44 in)	1120 mm (44 in)	960 mm (37.8 in)	960 mm (37.8 in)
Height	940 mm (37 in)	1180 mm (46.5 in)	940 mm (37 in)	1180 mm (46.5 in)

STORAGE

Unless otherwise specified, fiberglass products should be stored in a dry, cool and moisture-proof area. Room temperature and humidity should always be maintained at 15°C – 35°C, 35% – 65% respectively.

Best used within 12 months after production date. Fiberglass products should remain in their original packaging until just prior to use.

To ensure safety and avoid damage to the product, the pallets should not be stacked more than two layers high. When the pallets are stacked in two layers, care should be taken to correctly and smoothly move the top pallet.